



Reg No. : 2003/096209/23 | VAT No. : 4090216435

Steinhoff Industrial Park, George

RubberClad™

COLOR: Off-White

BASIC USES:

- Economical initial layers option for System 5100

PRODUCT DESCRIPTION:

RubberClad™ combines all of the ingredients of Topps Seal® Base Coat to lock out moisture and lock in PolyCore™ reinforcing membrane as System 5100 is installed across sloped built-up and concrete roofing. This most economical blend combines ingredients to take advantage of the properties added by the PolyCore center and builds sufficient mil thickness at the lowest cost possible. Its maximized adhesive package produces the tight bond to the original roof which characterizes a System 5100 completed roof overlay, utilizing the existing roof as its base and eliminating costly unnecessary tear-off and replacement.

FEATURES:

- All rubber permanent flexibility
- Excellent weather, pollution, and acid rain resistance
- Seamless encapsulation of the all polyester reinforcement

**WET MATERIAL
Typical Product
Characteristics**

Viscosity	115 – 120 K.U.
Weight per gallon	4.0 – 4.5 kg.
Solids	55% min.
Flashpoint of solvent	40°C
VOC	500 g/l

**CURED COATING
Typical
Performance
Properties**

Ultimate Elongation	400%
Ultimate tensile strength	5.5 N/mm ²
Peel Adhesion	2.9 pli
Water vapor permeability	0.35 perms
Moisture absorption (7 day submersion)	<0.5% max
Service temperature	-40° - 60°C

The spreading rate (m²/L) is approximate only as it may be influenced by profile, textured or porous surfaces, and application method and tools.